


Durisol - DSs 37,5/12

Parameters						
Application of product			building system for construction above ground			
Production			Slovakia: Bratislava, Austria: Mautern			
According to norm: EN 15498			length	width	height	
Dimensions	Declared dimension		mm	500	375	250
	Concrete core size		mm	120		
	Minimal area of partition wall cutout		cm ²	3 x 50		
	Surface of concrete core in the masonry layer		cm ² /m	810		
	Surface of concrete core between masonry layers (with mandatory offset of 25 cm)		cm ² /m	690		
Weight	Weight		kg/pcs	15		
	Weight of wall per m ² (with concrete filling 2 200 kg/m ³) without plaster		kg/m ²	326		
	Oven-dry density of block		kg/m ³	550		
Application data	Application rate		ks/m ²	8		
	Requirement of concrete filling		[liter/block]	11,7		
	Requirement of concrete filling		liter/m ²	94		
	Estimated requirement of construction steel		kg/m ²	0,25		
	Standard packaging		pcs/palette	30		
Thermal parameters	Thermal resistance	R	m ² k/W	5,26		
	Coefficient of heat conductivity (with plaster)	U	W/m ² K	0,18		
Other parameters	Fire protection class		class	B-s1, d0		
	Fire resistance (with plaster)		-	REI 180		
	Flexural strenght of the outer layer		N/mm ²	NPD		
	Sound reduction index	R _w (C _{ce})	dB	NPD		
	Freeze resistance		-	freeze resistant		
	Distortion under moisture		mm/m	NPD		
	Expenditure of work		h/m ²	0,5 - 0,7 (dependent on design)		



Product description
Block with integrated thermal insulation. Has to be filled with concrete to form a complete wall.

Thermal insulation Expanded polystyrene

Range of application
Construction of load-bearing walls. Construction of outer walls of detached houses, semi-detached houses, multiple story residential buildings, office buildings, industrial buildings.

Origin of wood in CZE

Complement

Universal block

